

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 July 2002 (18.07.2002)

PCT

(10) International Publication Number
WO 02/055620 A2

(51) International Patent Classification⁷: **C09D 167/02**

(21) International Application Number: PCT/EP01/14888

(22) International Filing Date:
17 December 2001 (17.12.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
00128097.3 21 December 2000 (21.12.2000) EP

(71) Applicant (for all designated States except US): **UCB, S.A.** [BE/BE]; Allée de la Recherche, 60, B-1070 Bruxelles (BE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **MOENS, Luc** [BE/BE]; Ijstvogellaan 30, B-1640 Sint-Genesius-Rode (BE). **KNOOPS, Nele** [BE/BE]; Blokweg 12, B-3020 Herent (BE). **MAETENS, Daniel** [BE/BE]; Avenue René Comhaire 108, B-1070 Bruxelles (BE).

(74) Agent: **ROELANTS, François**; UCB, S.A., Intellectual Property Department, Allée de la Recherche, 60, B-1070 Bruxelles (BE).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- without international search report and to be republished upon receipt of that report
- entirely in electronic form (except for this front page) and available upon request from the International Bureau

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: POWDERED THERMOSETTING COMPOSITION FOR COATINGS

(57) Abstract: The present invention relates to powdered thermosetting compositions including a binder which comprises a carboxyl group containing amorphous isophthalic acid containing polyester, a carboxyl group containing semi-crystalline polyester, at least 10 parts by weight, based on the total weight of the binder, of a specific glycidyl group containing acrylic copolymer and a curing agent having functional groups reactive with the polyesters' carboxyl groups. The powdered thermosetting compositions are useful for the preparation of powdered paints and varnishes which give low gloss coatings having an outstanding flow, a remarkable weatherability and excellent mechanical properties.

WO 02/055620 A2

Powdered thermosetting composition for coatings

The present invention relates to powdered thermosetting compositions comprising as binder a co-reactable particulate mixture of a carboxyl group containing amorphous polyester, a carboxyl
5 group containing semi-crystalline polyester, a glycidyl group containing acrylic copolymer and a curing agent having functional groups reactive with the polyesters' carboxyl groups. The invention also relates to the use of said compositions for the preparation of powdered paints and varnishes which give matt (low-gloss) coatings providing an outstanding flow, a remarkable weatherability and excellent mechanical properties. The invention further relates to the matt
10 coatings obtainable from said compositions.

Powdered thermosetting compositions are widely used as paints and varnishes for coating the most various articles. These powders have numerous advantages. On the one hand the problems associated with solvents are completely eliminated and on the other hand the powders are not
15 wasted, since only the powder in direct contact with the article is retained on the article, any excess powder being, in principle, entirely recoverable and reusable. For these and other reasons, powdered coating compositions are preferred to coating compositions in the form of solutions in e.g. organic solvents.

20 Powdered coating compositions should give coatings which have a good adhesion to metal substrates like steel or aluminium, a nice flow without defects and orange peel, a good flexibility and weatherability as well as a good chemical resistance. Besides, powdered coating compositions should exhibit a sufficiently high glass transition temperature to avoid reagglomeration during handling, transportation and storage.

25

The majority of today's coating compositions provide coatings having a high gloss after fusion and curing. The gloss measured at an angle of 60° in accordance with ASTM D523 is in fact often equal to or indeed even greater than 90%.

30 For example, WO 97/20895 discloses powdered thermosetting compositions including a binder consisting of a mixture of semi-crystalline and amorphous polyesters containing carboxyl groups, and a cross-linking agent with functional groups capable of reacting with the carboxyl groups of the polyesters. The powdered thermosetting compositions are useful for preparing powdered varnishes and paints and provide coatings having a remarkable weather resistance,
35 high gloss and excellent mechanical properties.

CONFIRMATION COPY

WO 91/14745 discloses a thermosetting powder coating composition comprising as binder a co-reactable particulate mixture of a carboxylic acid-functional semi-crystalline polyester component and a curing agent having groups reactable with carboxylic acid groups. The composition may, if desired, include an amorphous polyester, which is said to afford coatings with improved weathering performance and improved resistance to gloss reduction of the coating during outdoor exposure. So-called "hybrid" powder coating compositions comprise an epoxy resin as a co-reactable curing agent. Polyglycidyl-functional acrylic polymers are mentioned among numerous other epoxy resins. The coatings obtained from these thermosetting powder compositions exhibit a high gloss.

While powdered compositions which provide high gloss coatings with good appearance and mechanical properties as well as good weather resistance are known, there is an increasing demand for powdered paints and varnishes which provide matt coatings of good quality, for example for coating certain accessories in the automotive industry, such as wheel rims, bumpers and the like, or for coating metal panels and beams used in construction.

Thus, various methods for manufacturing powdered paints and varnishes that provide matt coatings, have been proposed.

According to one of these methods one or more matting agents, such as described in US 4,242,253, are introduced into the powdered composition, in addition to the binder and conventional pigments.

US 3,842,035 relates to a heat curable powder coating composition which, upon curing, gives a matt finish and which comprises a mixture of a slow curing and a fast curing thermosetting powder composition. The two compositions are extruded separately before dry-blending.

WO 92/01756 describes powder coating compositions comprised of one or more semi-crystalline hydroxyl polyesters, one or more amorphous polyesters and one or more hydroxyl acrylic polymers and a blocked polyisocyanate cross-linking agent. Coatings of the compositions on shaped metal articles exhibit an ASTM D-523-85 60° gloss value of not greater than 35.

In EP-A-0 551 064 powdered thermosetting compositions comprising as binder a mixture of a linear carboxyl group containing polyester and a glycidyl group containing acrylic copolymer are described. The acrylic polymer must have a number averaged molecular weight (Mn) of

4000 to 10000 in order to obtain coatings with useful physical properties. The compositions are useful for the preparation of powdered paints and varnishes which produce matt finishes having a gloss value measured at an angle of 60° in accordance with ASTM D523 equal to or less than 15.

5

Despite the existing variability of methods for producing matt finishes, experience has shown that these methods are all subject to one or more disadvantages attributed to problems of processing, as well as to overall coating performances. Problems are particularly relating to reproducibility and reliability of the gloss value.

10

There is thus still a need for powdered thermosetting compositions, capable of producing matt (low-gloss) coatings which do not exhibit the defects and drawbacks of the prior art.

15

In addition there is a sustained effort to improve flexibility and weatherability of the matt finishes in order to get them appropriate for applications such as coil coating, for example intended for outdoor construction purposes, especially for use in regions having a tropical climate.

20

However, when matt finishes are considered, no method is known today for preparing thermosetting powdered compositions from a single extrusion, which, upon curing, provide criteria such as outstanding flow, remarkable weatherability and excellent flexibility and for which low gloss values are perceived in a reproducible and reliable manner.

25

According to the present invention, it now has been surprisingly found that by using as binder a co-reactable particulate mixture of a carboxyl group containing amorphous isophthalic acid containing polyester, a carboxyl group containing semi-crystalline polyester, at least 10 parts by weight of a specific glycidyl group containing acrylic copolymer and a curing agent having functional groups reactive with the polyesters' carboxyl groups, it is possible to obtain powdered thermosetting compositions which produce coatings exhibiting the desired characteristics.

30

Thus, according to the present invention there is provided a powdered thermosetting composition including a binder which comprises

- (a) a carboxyl group containing amorphous isophthalic acid containing polyester,
- 35 (b) a carboxyl group containing semi-crystalline polyester.

- (c) at least 10 parts by weight, based on the total weight of the binder, of a glycidyl group containing acrylic copolymer, said copolymer comprising at least 10 mole% of a glycidyl group containing monomer and having a number averaged molecular weight (M_n) of at least 10000, and
- 5 (d) a curing agent having functional groups reactive with the polyesters' carboxyl groups.

The present composition is useful for preparing low-gloss coatings, i.e. coatings having a gloss value measured at an angle of 60° in accordance with ASTM D523 equal to or less than 40, preferably less than 35.

10

In the sense of the present application the term "isophthalic acid containing polyester" refers to a polyester which is composed of at least 10 mole% of isophthalic acid, preferably at least 50 mole%, based on the total acid constituents of the polyester.

- 15 The amorphous polyester and the semi-crystalline polyester independently may be linear or branched.

The carboxyl group containing amorphous polyester (a) of the present composition is preferably composed of, referring to the acid constituents, from 10 to 100 mole% of isophthalic acid, preferably 50 to 100 mole% and from 90 to 0 mole% of another diacid, such as an aliphatic, cycloaliphatic or aromatic diacid, and, referring to the alcohol constituents, from 70 to 100 mole% of neopentyl glycol and/or 2-butyl-2-ethyl-1,3-propanediol and from 30 to 0 mole% of of another diol, such as an aliphatic or cycloaliphatic diol. Branching of the amorphous polyester can be obtained by incorporation of a polyacid or polyol.

25

The acid constituent of the amorphous polyester, which is not the isophthalic acid, may preferably be selected from one or more aliphatic, cycloaliphatic or aromatic diacids, such as fumaric acid, maleic acid, phthalic acid, terephthalic acid, 1,4-cyclohexanedicarboxylic acid, 1,3-cyclohexanedicarboxylic acid, 1,2-cyclohexanedicarboxylic acid, succinic acid, adipic acid, 30 glutaric acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, 1,12-dodecanedioic acid, etc., or the corresponding anhydrides.

- Incorporation of e.g. up to 15 mole% relative to the isophthalic acid, of polyacids having at least three carboxylic acid groups such as trimellitic acid or pyromellitic acid or their corresponding anhydrides or mixtures thereof, induces branching of the polyester.
- 35

The glycol constituent of the amorphous polyester, which is not the neopentyl glycol and/or 2-butyl-2-ethyl-1,3-propanediol, may preferably be selected from one or more aliphatic or cycloaliphatic glycols, such as ethylene glycol, propylene glycol, 1,4-butanediol, 1,6-hexanediol, 1,4-cyclohexanediol, 1,4-cyclohexanedimethanol, 2-methyl-1,3-propanediol, 5 hydrogenated Bisphenol A, hydroxypivalate of neopentyl glycol, etc.

Incorporation of e.g. up to 15 mole % relative to the neopentyl glycol and/or 2-butyl-2-ethyl-1,3-propanediol, of trifunctional or tetrafunctional polyols such as trimethylolpropane, di-trimethylolpropane, pentaerythritol or mixtures thereof, induces branching of the polyester.

10

The carboxyl group containing amorphous polyesters (a) of the present composition preferably have an acid number (AN) from 15 to 100 mg KOH/g and in particular from 30 to 70 mg KOH/g.

15 The carboxyl group containing amorphous polyesters are advantageously further characterised by:

- a number averaged molecular weight (M_n) ranging from 1100 to 15000 and preferably from 1600 to 8500, measured by gel permeation chromatography (GPC);
- 20 - a glass transition temperature (T_g) from 40 to 80°C, measured by Differential Scanning Calorimetry according to ASTM D3418 with a heating gradient of 20°C per minute; and
- an ICI (cone/plate) viscosity accordingly to ASTM D4287-88, measured at 200°C
- 25 ranging from 5 to 15000 mPa.s.

The carboxyl group containing amorphous polyester may fulfill one or more of the above conditions for its acid number, its number averaged molecular weight, its glass transition temperature and its ICI viscosity. Preferably, the amorphous polyester, however, fulfills all of 30 these requirements.

The carboxyl group containing semi-crystalline polyester (b) of the present composition is preferably composed of, referring to the acid constituents, from 75 to 100 mole% of 1,4-cyclohexanedicarboxylic acid, or terephthalic acid, or mixtures thereof and from 25 to 0 mole% 35 of another diacid, such as an aliphatic, cycloaliphatic or aromatic diacid, and, referring to the

alcohol constituents, from 75 to 100 mole% of an aliphatic non-branched diol and from 25 to 0 mole% of another aliphatic or cycloaliphatic diol.

Alternatively, the semi-crystalline polyester may be composed of, referring to the acid constituents, from 75 to 100 mole% of linear non-branched aliphatic diacid and from 25 to 0 mole% of another diacid, such as an aliphatic, cycloaliphatic or aromatic diacid, and referring to the alcohol constituents, from 75 to 100 mole% of aliphatic non-branched or a cycloaliphatic diol and from 25 to 0 mole% of another aliphatic diol. Branching of the semi-crystalline polyester can be obtained by incorporation of a polyacid or a polyol or a mono-carboxylic acid having at least two hydroxyl groups or a mixture of them.

If the acid constituent of the semi-crystalline polyester of the present composition is for 75 to 100 mole% composed of 1,4-cyclohexanedicarboxylic acid, or terephthalic acid, or mixtures thereof, the 25 to 0 mole% of another diacid may be selected from fumaric acid, maleic acid, phthalic acid, isophthalic acid, terephthalic acid, 1,3-cyclohexanedicarboxylic acid, 1,2-cyclohexanedicarboxylic acid, succinic acid, adipic acid, glutaric acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, 1,12-dodecanedioic acid, etc., or the corresponding anhydrides.

In this case, the alcohol constituent of the semi-crystalline polyester of the present composition preferably is for 75 to 100 mole% composed of an aliphatic non-branched diol such as ethylene glycol, 1,3-propanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,7-heptanediol, 1,8-octanediol, 1,9-nonanediol, 1,10-decanediol, 1,12-dodecanediol, 1,14-tetradecanediol, 1,16-hexadecanediol, etc. used in mixture or alone, and for 25 to 0 mole% of another aliphatic or cycloaliphatic glycol, such as propylene glycol, neopentyl glycol, 2-methyl-1,3-propanediol, 2-butyl-2-ethyl-1,3-propanediol, hydrogenated Bisphenol A, hydroxypivalate of neopentyl glycol, 1,4-cyclohexanediol, 1,4-cyclohexanedimethanol, etc.

Otherwise, if the acid constituent of the semi-crystalline polyester of the present composition is for 75 to 100 mole% composed of linear non-branched aliphatic diacid, these may be selected from succinic acid, adipic acid, glutaric acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, 1,12-dodecanedioic acid, etc. used in mixture or alone. Preferably the linear non-branched aliphatic diacid contains from 4 to 9 carbon atoms. The 25 to 0 mole% of another aliphatic, cycloaliphatic or aromatic diacid may be selected from fumaric acid, maleic acid, terephthalic acid, phthalic acid, isophthalic acid, 1,2-cyclohexanedicarboxylic acid, 1,3-cyclohexanedicarboxylic acid, 1,4-cyclohexanedicarboxylic acid, etc., or the corresponding anhydrides.

In this case, the glycol constituent of the semi-crystalline polyester of the present composition is for 75 to 100 mole% composed of cycloaliphatic diol such as 1,4-cyclohexanedimethanol, 1,4-cyclohexanediol or hydrogenated Bisphenol A, etc. used in mixture or alone, or aliphatic non-
5 branched diol such as of ethylene glycol, 1,3-propanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,7-heptanediol, 1,8-octanediol, 1,9-nonanediol, 1,10-decanediol, 1,14-tetradecanediol, 1,16-hexadecanediol, etc. used in mixture or alone, and for 25 to 0 mole% of
10 of another aliphatic diol or polyol, such as of propylene glycol, neopentyl glycol, 2-methyl-1,3-propanediol, 2-butyl-2-ethyl-1,3-propanediol, hydroxypivalate of neopentyl glycol, 1,4-cyclohexanediol, 1,4-cyclohexanedimethanol, hydrogenated Bisphenol A, ethylene glycol, 1,3-propanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,7-heptanediol, 1,8-octanediol, 1,9-nonanediol, 1,10-decanediol, 1,14-tetradecanediol, 1,16-hexadecanediol, etc.

Incorporation of e.g. up to 15 mole percentage based on the total of 1,4-
15 cyclohexanedicarboxylic acid, or terephthalic acid, or non-branched aliphatic diacid, of polyacids having at least three carboxylic acid groups such as trimellitic acid or pyromellitic acid or their corresponding anhydrides, or of e.g. up to 15 mole percentage based on the total of aliphatic non-branched diol or cycloaliphatic diol, of trifunctional or tetrafunctional polyols such as trimethylolpropane, di-trimethylolpropane, pentaerythritol or mixtures of them, induces
20 branching of the semi-crystalline polyesters.

The carboxyl group containing semi-crystalline polyesters of the present composition preferably have an acid number (AN) from 10 to 100 mg KOH/g and in particular from 15 to 80 mg
25 KOH/g.

The carboxyl group containing semi-crystalline polyesters are advantageously further characterised by:

- a number averaged molecular weight (M_n) ranging from 1100 to 17000 and preferably
30 from 1400 to 11200, measured by gel permeation chromatography (GPC);
- a fusion zone from 30 to 150°C, measured by Differential Scanning Calorimetry (DSC) according to ASTM D3418 with a heating gradient of 20°C per minute;

- a glass transition temperature (T_g) from -50 to $+50^\circ\text{C}$, measured by Differential Scanning Calorimetry (DSC) according to ASTM D3418 with a heating gradient of 20°C per minute;
- 5 - a degree of crystallinity, measured by Differential Scanning Calorimetry (DSC) according to ASTM D3415 of at least 5 J/g and preferably at least 10 J/g ; and
- an ICI (cone/plate) viscosity according to ASTM D4287-88, measured at 175°C ranging from 5 to 20000 mPa.s .

10

The carboxyl group containing semi-crystalline polyester may fulfill one or more of the above conditions for its acid number, its number averaged molecular weight, its fusion zone, its glass transition temperature, its degree of crystallinity and its ICI viscosity. Preferably, the semi-crystalline polyester, however, fulfills all of the above requirements.

15

The glycidyl group containing acrylic copolymer (c) of the present composition is preferably composed of 10 to 90 mole\% of a glycidyl group containing monomer and from 90 to 10 mole\% of other monomers copolymerisable with the glycidyl group containing monomer.

- 20 The glycidyl group containing monomer used in the acrylic copolymer of the present composition may be selected from, for example, glycidyl acrylate, glycidyl methacrylate, methyl glycidyl methacrylate, methyl glycidyl acrylate, 3,4-epoxycyclohexylmethyl (meth)acrylate and acrylic glycidyl ether. These monomers can be used singly or in combination of two or more.

25

The other monomers of the acrylic copolymer copolymerisable with the glycidyl group containing monomer may be selected from:

- 40 to $100\text{ mole percentage}$ of acrylic or methacrylic ester monomers such as methyl
- 30 acrylate, ethyl acrylate, n-propyl acrylate, isopropyl acrylate, n-butyl acrylate, n-decyl acrylate, methyl methacrylate, ethyl methacrylate, n-propyl methacrylate, isopropyl methacrylate, n-butyl methacrylate, isobutyl methacrylate, n-amyl methacrylate, n-hexyl methacrylate, isoamyl methacrylate, allyl methacrylate, sec-butyl methacrylate, tert-butyl methacrylate, 2-ethylbutyl methacrylate, cinnamyl methacrylate, crotyl
- 35 methacrylate, cyclohexyl methacrylate, cyclopentyl methacrylate, methallyl

methacrylate, n-octyl methacrylate, 2-ethylhexyl methacrylate, 2-phenylethyl methacrylate and phenyl methacrylate.

- 0 to 60 mole percentage of other ethylenically unsaturated copolymerisable monomers such as styrene, alkyl-substituted styrenes and chloro-substituted styrenes, acrylonitrile, vinyl chloride, vinylidene fluoride and vinyl acetate.

The glycidyl group containing acrylic copolymers of the present composition preferably have an epoxy equivalent weight of 0.3 to 5.0 and preferably from 1.0 to 3.0 milliequivalents of epoxy/gram of polymer.

The glycidyl group containing acrylic copolymers may further be characterised by:

- a number averaged molecular weight (M_n) ranging from 10000 to 25000, preferably 10.100 to 25.000, measured by gel permeation chromatography (GPC);
- a glass transition temperature (T_g) from 40 to 85°C, measured by Differential Scanning Calorimetry (DSC), according to ASTM D3418 with a heating gradient of 20°C per minute;
- an ICI (cone/plate) viscosity determined by the ICI method at 200°C ranging from 50 to 50000 mPa.s.

The glycidyl group containing acrylic copolymer may fulfill one or more of the above conditions for its epoxy equivalent weight, its number averaged molecular weight, its glass transition temperature and its ICI viscosity. Preferably, the acrylic copolymer, however, fulfills all of the above requirements.

The curing agent in accordance to the present invention, having functional groups reactive with the polyesters' carboxyl groups, may be selected from:

- polyepoxy compounds preferably being solid at room temperature and containing at least two epoxy groups per molecule such as, for example, triglycidyl isocyanurate like the one marketed under the name Araldite PT810 (Ciba) or the epoxy resin Araldite PT910 (Ciba); and

- B-hydroxyalkylamide group containing compounds which preferably contain at least one, more preferably two bis(B-hydroxyalkyl)amide groups, for example, those mentioned in US 4,727,111, US 4,076,917, EP-A-0 322 834 and EP-A-0 473 380.

5 The carboxyl group containing amorphous polyester and the carboxyl group containing semi-crystalline polyester of the present composition are preparable using conventional esterification techniques well known in the art. The polyesters are prepared according to a procedure consisting of one or more reaction steps.

10 For the preparation of these polyesters, a conventional reactor equipped with a stirrer, an inert gas (nitrogen) inlet, a thermocouple, a distillation column connected to a water-cooled condenser, a water separator and a vacuum connection tube can be used.

The esterification conditions used to prepare the polyesters are conventional, namely a standard
15 esterification catalyst, such as dibutyltin oxide, dibutyltin dilaurate, n-butyltin trioctoate, sulphuric acid or a sulphonic acid, can be used in an amount from 0.05 to 1.50% by weight of the reactants and optionally, colour stabilisers, for example, phenolic antioxidants such as Irganox 1010 (Ciba) or phosphonite- and phosphite-type stabilisers such as tributylphosphite, can be added in an amount from 0 to 1% by weight of the reactants.

20

Polyesterification is generally carried out at a temperature which is gradually increased from 130°C to about 190 to 250°C, first under normal pressure, then, when necessary, under reduced pressure at the end of each process step, while maintaining these operating conditions until a polyester is obtained, which has the desired hydroxyl and/or acid number. The degree of
25 esterification is followed by determining the amount of water formed in the course of the reaction and the properties of the obtained polyester, for example the hydroxyl number, the acid number, the molecular weight or the viscosity.

When polyesterification is complete, cross-linking catalysts can optionally be added to the
30 polyester while it is still in the molten state. These catalysts are added in order to accelerate cross-linking of the thermosetting powder composition during curing. Examples of such catalysts include amines (e.g. 2-phenylimidazoline), phosphines (e.g. triphenylphosphine), ammonium salts (e.g. tetrabutylammonium bromide or tetrapropylammonium chloride), phosphonium salts (e.g. ethyltriphenylphosphonium bromide or tetrapropylphosphonium
35 chloride). These catalysts are preferably used in an amount of 0 to 5% with respect of the weight of the polyester.

The glycidyl group containing acrylic copolymer is preparable by conventional polymerisation techniques, either in mass, in emulsion, or in solution in an organic solvent. The nature of the solvent is very little of importance, provided that it is inert and that it readily dissolves the monomers and the synthesised copolymer. Suitable solvents include toluene, ethyl acetate, butyl acetate, xylene, etc. The monomers are copolymerised in the presence of a free radical polymerisation initiator (benzoyl peroxide, dibutyl peroxide, azo-bis-isobutyronitrile, and the like) in an amount representing 0.1 to 4.0% by weight of the monomers.

To achieve a good control of the molecular weight and its distribution, a chain transfer agent, preferably of the mercaptan type, such as n-dodecylmercaptan, t-dodecanethiol, isooctylmercaptan, or of the carbon halide type, such as carbon tetrabromide, bromotrichloromethane, etc., is also added in the course of the reaction. The chain transfer agent is used in amounts of up to 10% by weight of the monomers used in the copolymerisation.

A cylindrical, double walled reactor equipped with a stirrer, a condenser, an inert gas (nitrogen, for example), inlet and outlet, and metering pump feed systems are generally used to prepare the glycidyl group containing acrylic copolymer.

Polymerisation can be carried out under conventional conditions. Thus, when polymerisation is carried out in solution, for example, an organic solvent is introduced into the reactor and heated to reflux temperature under an inert gas atmosphere (nitrogen, carbon dioxide, and the like) and a homogeneous mixture of the required monomers, free radical polymerisation initiator and chain transfer agent, when needed, is then added to the solvent gradually over several hours.

The reaction mixture is then maintained at the indicated temperature for some hours, while stirring. The copolymer obtained is subsequently freed from the solvent in vacuo.

Preferably, the binder system of the thermosetting powdered composition of the present invention comprises based on the total weight of the binder:

- 2 to 88.5, preferably 40 to 80 and more preferably 45 to 75 parts by weight of the carboxyl group containing amorphous isophthalic acid containing polyester,
- 1 to 85, preferably 5 to 40 and more preferably 10 to 30 parts by weight of the carboxyl group containing semi-crystalline polyester,

- 10 to 60, preferably 15 to 40 and more preferably 20 to 35 parts by weight of the glycidyl group containing acrylic copolymer, and
- 0.5 to 10.0, preferably 1 to 5 and more preferably 2 to 3 parts by weight of the curing agent having functional groups reactive with the polyesters' functional groups.

The binder system of the thermosetting composition of the present invention is preferably composed in such a way that for each equivalent of carboxyl group present in the amorphous polyester (a) and semi-crystalline polyester (b) there is between 0.3 and 2.0 and preferably between 0.6 and 1.7 equivalents of epoxy groups from the acrylic copolymer (c) and between 0.2 and 1.2 and preferably between 0.4 and 1.0 equivalents of reactive functional groups of the curing agent (d).

The thermosetting polyester blend (a & b), when needed, can be obtained by dry blending the amorphous and the semi-crystalline polyester using a mechanical mixing procedure as available for the premixing of the powder paint constituents.

Alternatively the amorphous and the semi-crystalline polyester can be blended in the melt using a conventional cylindrical double-walled reactor or by extrusion such as with the Betol BTS40.

In addition to the essential components described above, compositions within the scope of the present invention can also include one or more additive(s) such as catalysts, fillers, flow control agents such as Resiflow PV5 (Worlee), Modaflow (Monsanto), Acronal 4F (BASF), etc., and degassing agents such as benzoin (BASF) etc. To the formulation UV-light absorbers such as Tinuvin 900 (Ciba), hindered amine light stabilisers represented by Tinuvin 144 (Ciba), other stabilising agents such as Tinuvin 312 and 1130 (Ciba), antioxidants such as Irganox 1010 (Ciba) and stabilisers from the phosphonite or phosphite type can be added.

Both, pigmented systems as well as clear lacquers can be prepared.

A variety of dyes and pigments can be utilised in the composition of this invention. Examples of useful pigments and dyes are metallic oxides such as titaniumdioxide, ironoxide, zincoxide and the like, metal hydroxides, metal powders, sulphides, sulphates, carbonates, silicates such as ammoniumsilicate, carbon black, talc, china clay, barytes, iron blues, lead blues, organic reds, organic maroons and the like.

The components of the composition according to the invention may be mixed by dry blending in a mixer or blender (e.g. drum mixer). The premix is then homogenised at temperatures ranging from 70 to 150°C in a single screw extruder such as the BUSS-Ko-Kneter or a double screw extruder such as the PRISM or APV. The extrudate, when cooled down, is grounded to a powder with a particle size preferably ranging from 10 to 150 µm.

The powdered composition may be deposited on the substrate by use of a powder gun such as an electrostatic CORONA gun or TRIBO gun. On the other hand well known methods of powder deposition such as the fluidised bed technique can be used. After deposition the powder is heated to a temperature between 160 and 320°C, causing the particles to flow and fuse together to form a smooth, uniform, continuous, uncratered coating on the substrate surface.

Thus, the present invention further relates to the use of the above described compositions as powdered varnish or paint or for the preparation of a powdered varnish or paint. The invention further relates to the powdered varnishes or paints consisting of or comprising the present powdered thermosetting composition.

Furthermore, the present invention relates to a method of preparing a coating on a substrate comprising the steps of applying the above varnish or paint to the substrate and heating the coated substrate to fuse and cure the powdered varnish or paint to obtain the coating.

Furthermore, the present invention also refers to a coating preparable by the above method and a substrate entirely or partially coated with such coating.

The following examples are submitted for a better understanding of the invention but are not intended to restrict the invention thereto.

If not otherwise stated, all amounts are given in parts by weight.

Besides the abbreviations already defined above, Mw stands for weight-average molecular weight, OHN stands for hydroxyl number and Tm stands for fusion zone.

Example 1

Preparation of a glycidyl group containing acrylic copolymer

80 parts of n-butyl acetate are brought in a double walled flask of 5 l equipped with a stirrer, a water cooled condenser, an inlet for nitrogen and a thermocouple attached to a thermoregulator.

The flask content is then heated and stirred continuously while nitrogen is purged through the solvent. At a temperature of 125°C a mixture of 0.8 parts of tert-butylperoxybenzoate in 20 parts of n-butyl acetate are fed in the flask during 215 minutes with a peristaltic pump. 5 minutes after this start another pump is started with the feeding of a mixture of 22 parts of styrene, 24 parts of glycidyl methacrylate, 40 parts of butyl methacrylate and 14 parts of methyl methacrylate, during 180 minutes. The synthesis takes 315 minutes.

After evaporation of the n-butyl acetate an acrylic copolymer with the following characteristics is obtained:

ICI200°C (cone/plate)	16000 mPa.s
Mn	15000
Mw	38200

Examples 2 to 6

Accordingly the procedure as described in example 1, the acrylic copolymers of example 2 to example 6, having the compositions as in table 1, were prepared.

Table 1

	example 2*	example 3	example 4	example 5	example 6*
styrene	22	22	25.5	23	27.2
glycidyl methacrylate	24	24	12	24	6
butyl methacrylate	40	40	46.3	15	49.5
methyl methacrylate	14	14	16.2	38	17.3
n-butyl peroxybenzoate	2.0	0.6	0.8	0.8	0.8
Mn	9300	22600	16600	17000	15500
Mw	20400	52400	39800	40500	38600
ICI200°C, mPa.s	4200	30000	24000	40000	17000

* Comparative examples

Ex 2 and 6 are comparative examples because the number averaged molecular weight (Mn) of the copolymer obtained in Ex 2 is below 10000 and the glycidyl methacrylate content of the copolymer of Ex 6 is below 10 mole%.

Example 7:

Synthesis of an isophthalic acid containing amorphous polyester

424.0 parts of neopentyl glycol are placed in a conventional four neck round bottom flask equipped with a stirrer, a distillation column connected to a water cooled condenser, an inlet for nitrogen and a thermometer attached to a thermoregulator.

The flask contents are heated, while stirring under nitrogen, to a temperature of circa 130°C at which point 217.7 parts of terephthalic acid and 355.2 parts of isophthalic acid and 2.2 parts of n-butyltintriocatoate are added. The heating is continued gradually to a temperature of 230°C. Water is distilled from the reactor from 180°C on. When distillation under atmospheric pressure stops, a vacuum of 50 mm Hg is gradually applied. After three hours at 230°C and 50 mm Hg, the following characteristics are obtained:

15	AN	4 mg KOH/g
	OHN	83 mg KOH/g

To the first step prepolymer standing at 200°C, 147.7 parts of isophthalic acid are added. Thereupon, the mixture is gradually heated to 230°C. After a 2 hour period at 230°C and when the reaction mixture is transparent, a vacuum of 50 mm Hg is gradually applied. After 3 hours at 230°C and 50 mm Hg, the following characteristics are obtained:

	AN	33 mg KOH/g
	OHN	3 mg KOH/g
25	ICI200°C (cone/plate)	3500 mPa.s
	Tg (DSC, 20°/min)	58°C

Example 8

Synthesis of an isophthalic acid containing amorphous polyester

30

A mixture of 395.9 parts of neopentyl glycol and 15.6 parts of trimethylolpropane is placed in a conventional four neck round bottom flask as for example 7.

The flask contents are heated, while stirring under nitrogen, to a temperature of circa 130°C at which point 692.8 parts of isophthalic acid, 36.5 parts of adipic acid and 2.5 parts of n-butyltintriocatoate are added. The heating is continued gradually to a temperature of 230°C. Water is

distilled from the reactor from 180°C on. When distillation under atmospheric pressure stops, a vacuum of 50 mm Hg is gradually applied. After three hours at 230°C and 50 mm Hg, the following characteristics are obtained:

5	AN	48 mg KOH/g
	OHN	3 mg KOH/g
	ICI200°C (cone/plate)	4900 mPa.s
	T _g (DSC, 20°/min)	59°C

10 Examples 9 to 10

Accordingly the procedure as described in example 8, the amorphous polyesters of examples 9 and 10, having the compositions as in table 2, are prepared.

15 Table 2

	example 9	example 10
neopentyl glycol	413.6	423.8
trimethylolpropane	9.3	
isophthalic acid	721.4	720.3
AN, mg KOH/g	32	30
OHN, mg KOH/g	3	2
ICI200°C, mPa.s	4500	3000
T _g (DSC 20°/min), °C	63	57

Example 11:

20 Synthesis of a cycloaliphatic semi-crystalline polyester

A mixture of 532.1 parts of 1,4-cyclohexanedimethanol, 15.9 parts of trimethylolpropane, 591.3 parts of adipic acid and 2.5 parts of n-butyltintriocatoate is placed in a reactor as for Example 8. The flask contents are heated, while stirring under nitrogen to a temperature of circa 140°C, at which point water is distilled from the reactor. The heating is continued gradually to a temperature of 220°C. When distillation under atmospheric pressure stops, 1.0 part of tributylphosphite and 1.0 part of n-butyltintriocatoate are added and a vacuum of 50 mm Hg is

gradually applied. After 5 hours at 220°C and 50 mm Hg, the following characteristics are obtained:

5	AN	22 mg KOH/g
	OHN	3 mg KOH/g
	ICI200°C (cone/plate)	6500 mPa.s
	Fusion zone	79 - 96°C

Examples 12 to 15

- 10 Accordingly the procedure as described in example 11, the semi-crystalline polyesters of examples 12 to 15, having the compositions as in table 3, are prepared.

Table 3

	example 12	example 13	example 14	example 15
1,4-cyclohexanedimethanol		448.1	477.3	
1,4-cyclohexanediol	467.3			
1,6-hexanediol				508.2
trimethylolpropane	15.5			15.9
adipic acid	638.5	165.3	319.8	628.4
1,12-dodecanoic acid		496.0	319.8	
AN, mg KOH/g	21	22	32	19
OHN, mg KOH/g	3	2	3	2
ICI, mPa.s	8800 (175°C)	3500 (150°C)	3000 (150°C)	3200 (150°C)
Tm, °C	39 - 47	67 - 77	70 - 80	48 - 55

15

Example 16

- 20 The polyesters and acrylic copolymers as illustrated above, are then formulated to a powder according to one of the formulations A or B as mentioned below.

Formulation A		Formulation B	
White paint formulation		Brown paint formulation	
Binder	74.00	Binder	78.33
Kronos 2310 (white pigment)	24.67	Bayferrox 130 (pigment)	4.44
Resiflow PV5 (flow control agent)	0.99	Bayferrox 3950 (pigment)	13.80
Benzoin (degassing agent)	0.34	Carbon Black FW2 (pigment)	1.09
		Resiflow PV5 (flow control agent)	0.99
		Benzoin (degassing agent)	0.35

- For the preparation of the powder formulation, the carboxyl group containing isophthalic acid containing amorphous polyester resin and the carboxyl group containing semi-crystalline polyester resin can be used as a blend or as separate resins. When used as a blend, blending is done by mixing the respective resins in the molten state using a conventional round bottom flask.
- 5 The powders are prepared first by dry blending of the different components and then by homogenisation in the melt using a PRISM 16 mm L/D 15/l twin screw extruder at an extrusion temperature of 85°C. The homogenised mix is then cooled and grinded in an Alpine UPZ100. Subsequently the powder is sieved to obtain a particle size between 10 and 110 µm. The powder thus obtained is deposited on chromated (Cr6+) aluminium H5005, DIN 50939 with a thickness of 1 mm, by electrostatic deposition using the GEMA - Volstatic PCG 1 spray gun. At a film thickness between 50 and 80 µm the panels are transferred to an air-ventilated oven, where curing proceeds for 15 minutes at a temperature of 200°C.
- 10
- 15

- The paint characteristics for the finished coatings obtained from formulation A (example 16 to 34) and from formulation B (examples 35 and 36) with binder compositions as specified in table 4, are summarized in tables 5 and 6.
- 20

Table 4

	1	2	3	4*	5*	6*
amorphous polyester	50.75	58.00	51.90	62.65	72.50	51.90
semi-crystalline polyester	21.75	14.50	13.00	26.85	-	22.20
acrylic copolymer	25.30	25.30	32.40	7.80	25.30	25.90
curing agent	2.20	2.20	2.70	2.70	2.20	-

* the binders 4,5 and 6 are comparative

5 Table 5

formulation A	binder	amorphous polyester	semi- crystalline polyester	acrylic co- polymers	curing agent	gloss	DI	RI
Ex 16	1	Ex 7	Ex 14	Ex 1	XL552	5	100	120
Ex 17	1	Ex 7	Ex 11	Ex 1	XL552	3	140	100
Ex 18	2	Ex 7	Ex 11	Ex 1	XL552	3	80	60
Ex 19	1	Ex 7	Ex 11	Ex 1	PT810	4	80	80
Ex 20	3	Ex 8	Ex 12	Ex 1	XL552	25	100	100
Ex 21	3	Ex 8	Ex 12	Ex 4	XL552	31	100	80
Ex 22	2	Ex 9	Ex 12	Ex 1	PT910	26	80	80
Ex 23	2	Ex 9	Ex 12	Ex 3	PT910	20	80	60
Ex 24	1	Ex 9	Ex 12	Ex 3	XL552	25	120	100
Ex 25	1	Ex 9	Ex 13	Ex 3	XL552	12	120	100
Ex 26	1	Ex 9	Ex 15	Ex 3	XL552	26	100	80
Ex 27	1	Ex 9	Ex 13	Ex 5	XL552	25	100	80
Ex 28	1	Ex 9	Ex 13	Ex 5	PT910	27	80	80
Ex 29	1	Ex 10	Ex 11	Ex 1	XL552	5	140	100
Ex 30*	1	Ex 10	Ex 11	Comp. Ex 2	XL552	85	140	120
Ex 31*	4	Ex 10	Ex 11	Ex 1	XL552	36	120	100
Ex 32*	5	Ex 10	-	Ex 1	XL552	6	20	0
Ex 33*	6	Ex 10	Ex 11	Ex 1	-	5	0	0
Ex 34*	1	Ex 10	Ex 11	Comp. Ex 6	XL552	90	100	100
Ex 35	1	Ex 9	Ex 11	Ex 1	XL552	28	120	100
Ex 36	2	Ex 8	Ex 12	Ex 5	XL552	30	100	80

* Examples 30 to 34 are comparative

In table 5:

Column 1: indicates the identification number of the formulation

Column 2: indicates the binder composition according to table 4

Column 3: indicates the type of amorphous polyester

Column 4: indicates the type of semi-crystalline polyester

Column 5: indicates the type of acrylic copolymer

Column 6: indicates the type of the curing agent

having functional groups being reactive with the polyesters' carboxyl groups where:

PT810 = Araldite 810 (Ciba)

= triglycidylisocyanurate

PT910 = Araldite 910 (Ciba)

= diglycidylterephthalate/

triglycidyltrimellitate mixture (75/25)

XL552 = Primid XL552 (EMS)

= N,N,N',N'-tetrakis-(2-hydroxyethyl)-
adipamide

Column 7: indicates the 60° gloss, measured according to ASTM D523

Column 8: indicates the direct impact strength according to ASTM D2794. The highest impact which does not crack the coating is recorded in kg.cm

Column 9: indicates the reverse impact strength according to ASTM D2794. The highest impact which does not crack the coating is recorded in kg.cm

Except for the formulation of reference example 31, where a wrinkle-type finish is observed, the coatings obtained from the different formulations all prove to have a very smooth visual perception, free of any defects.

The different coatings all have a flexibility of 0T or 1T maximum, according to the ASTM D4145-83 T-bending test, with the exception of the formulations of reference examples 32 and 33 where values higher than 3T, indicating a huge lack of flexibility, are perceived upon bending.

As clearly appears from table 5:

- 5 - the carboxyl group containing semi-crystalline polyester is necessary for providing flexibility to the coating (comparative example 32 versus example 29)
- decreasing the amount of semi-crystalline polyester reduces flexibility of the derived coating (example 18 versus example 17, example 23 versus example 24)
- 10 - the type of curing agent has no influence on the gloss and minor influence on flexibility (examples 17 & 19, 27 & 28)
- when the curing agent is omitted no influence on gloss, yet a huge influence on flexibility is perceived (comparative example 33 versus example 29)
- 15 - all glycidyl functionality of the acrylic copolymer, within the range as specified in the present invention, gives low gloss coatings without influencing flexibility (examples 20 & 21)
- 20 However, when an acrylic copolymer, having a too low glycidyl functionality (glycidyl group containing monomer content is lower than 10 mole percentage) as for the acrylic copolymer of example 6, is used, a high gloss value is observed (comparative example 34) for the resulting coating.
- 25 - modifying the acrylic copolymer composition (example 27) or the acrylic copolymer molecular weight (example 23) within the specifications of the present invention results in matt flexible finishes.
- 30 Only when the number average molecular weight is lower than 10000, as for the acrylic copolymer of example 2, a high gloss finish is observed (comparative example 30).

As appears from table 5, the powdered compositions according to the present invention (examples 16 to 29, 35 and 36) thus prove to satisfy a unique combination of properties. They are particularly useful to obtain low gloss coatings with an outstanding flexibility and flow.

The thermosetting powdered compositions according to the present invention are obtained from a single extrusion and give low gloss finishes in a reproducible and reliable way.

Moreover, the powders according to the present invention prove to satisfy an excellent outdoor
5 resistance comparable to the currently used nowadays commercial available powders.

In table 6, the relative 60° gloss values, recorded every 400 hours, according to ASTM D523, are reported for the coating obtained from examples 35 and 36, submitted to the Q-UV accelerated weathering test. In the same table (comparison) are given the weathering results of a
10 carboxylic acid functionalised amorphous polyester obtained by reacting 400,6 parts of neopentyl glycol, 22,3 parts of trimethylolpropane and 724,7 parts of isophthalic acid, in the same manner as in example 8.

This polyester has an AN of 32 mg KOH/g and a Tg of 59°C, determined by DSC with a heating rate of 20°C/min. This polyester is formulated in a 93/7 ratio with PT810 according to
15 the brown paint formulation as in formulation B. Thus, the comparison formulation did not contain any semi-crystalline polyester or acrylic copolymer.

In this table only gloss reductions until about 50% of the maximum value are mentioned. Weathering measurements are conducted in a very severe environment, i.e. the Q-UV
20 accelerated weathering tester (Q-Panel Co) according to ASTM G53-88 (standard practice for operating light and water exposure apparatus - fluorescent UV/condensation type - for exposure of nonmetallic materials).

For the results of table 6, coated panels have been subjected to the intermittent effects of
25 condensation (4 hours at 50°C) as well as the damaging effects of sunlight simulated by fluorescent UV-A lamps (340 nm, I = 0.77 W/m²/nm) (8 hours at 60°C).

Table 6

Hours	UV-A (340 nm, I = 0.77 W/m ² /nm)		
	example 36	example 35	Comparison
0	100	100	100
400	100	99	100
800	99	100	100
1200	98	97	97
1600	98	96	97
2000	97	97	97
2400	98	96	96
2800	99	94	95
3200	98	88	92
3600	95	85	89
4000	90	86	87
4400	87	84	84
4800	84	77	79
5200	78	66	76
5600	77	61	73
6000	74	52	67
6400	53	43	59
6800	54		54
7200	47		49
7600	40		

Claims:

1. Powdered thermosetting composition including a binder which comprises
 - 5 (a) a carboxyl group containing amorphous isophthalic acid containing polyester,
 - (b) a carboxyl group containing semi-crystalline polyester,
 - (c) at least 10 parts by weight, based on the total weight of the binder, of a glycidyl group containing acrylic copolymer, said copolymer comprising at least 10 mole% of a glycidyl group containing monomer and having a number averaged molecular weight
10 (Mn) of at least 10000, and
 - (d) a curing agent having functional groups reactive with the polyesters' carboxyl groups.
2. Composition according to claim 1, wherein the carboxyl group containing amorphous isophthalic acid containing polyester consists of 10-100 mole% isophthalic acid and 0-90
15 mole% of another diacid, based on the total of the acid constituents, and 70-100 mole% neopentyl glycol and/or 2-butyl-2-ethyl-1,3-propanediol and 0-30 mole% of another diol, based on the total of the alcohol constituents.
3. Composition according to claim 1 or 2, wherein the carboxyl group containing
20 amorphous isophthalic acid containing polyester further contains up to 15 mole% of polyacids relative to the isophthalic acid and/or up to 15 mole% of polyols, relative to the neopentylglycol and/or 2-butyl-2-ethyl-1,3-propanediol.
4. Composition according to any of claims 1 to 3, wherein the carboxyl group containing
25 amorphous isophthalic acid containing polyester has an acid number (AN) from 15-100 mg KOH/g, a number averaged molecular weight (Mn) from 1100 to 15000, a glass transition temperature (Tg) from 40-80°C and an ICI (cone/plate) viscosity at 200°C from 5-15000 mPa.s.
5. Composition according to any of the preceding claims, wherein the carboxyl group
30 containing semi-crystalline polyester consists of 75-100 mole% of 1,4-cyclohexanedicarboxylic acid, or terephthalic acid, or mixtures thereof, and 0-25 mole% of another diacid, based on the total of the acid constituents, and 75-100 mole% of an aliphatic non-branched diol and 0-25 mole% of another aliphatic or cycloaliphatic diol, based on the total of the alcohol constituents.
- 35 6. Composition according to any of claims 1-4, wherein the carboxyl group containing semi-crystalline polyester consists of 75-100 mole% of linear non-branched aliphatic diacid and

0-25 mole% of another diacid, based on the total of the acid constituents, and 75-100 mole% of an aliphatic non-branched or cycloaliphatic diol and 0-25 mole% of another aliphatic diol, based on the total of the alcohol constituents.

5 7. Composition according to claims 5 or 6, wherein the carboxyl group containing semi-crystalline polyester further contains up to 15 mole% of polyacids relative to the 1,4-cyclohexanedicarboxylic acid and/or terephthalic acid and/or linear non-branched aliphatic diacid and/or up to 15 mole% of polyols, relative to the 75-100 mole% of aliphatic non branched and/or cycloaliphatic diols.

10

8. Composition according to any of the preceding claims, wherein the carboxyl group containing semi-crystalline polyester has an acid number (AN) from 10-100 mg KOH/g, a number averaged molecular weight (Mn) from 1100-17000, a fusion zone from 30-150°C, a glass transition temperature (Tg) from -50 to 50°C, a degree of crystallinity of at least 5 J/g and
15 an ICI (cone/plate) viscosity at 175°C from 5-20000 mPa.s.

9. Composition according to any of the preceding claims, wherein the glycidyl group containing acrylic copolymer consists of 10-90 mole% of a glycidyl group containing monomer selected from the group consisting of glycidyl acrylate, glycidyl methacrylate, methyl glycidyl
20 acrylate, methyl glycidyl methacrylate, 3,4-epoxycyclohexylmethyl acrylate, 3,4-epoxycyclohexylmethyl methacrylate, acrylic glycidyl ether and mixtures thereof and 10-90 mole% of monomers copolymerisable with the glycidyl group containing monomers.

10. Composition according to any of the preceding claims, wherein the glycidyl group
25 containing acrylic copolymer has an epoxy equivalent weight of 0.3 to 5.0 milliequivalents of epoxy/gram of polymer, a number averaged molecular weight (Mn) from 10000-25000, a glass transition temperature (Tg) from 40-85°C and an ICI (cone/plate) viscosity at 200°C from 50-50000 mPa.s.

30 11. Composition according to any of the preceding claims, wherein the curing agent is a polyepoxy compound or a β -hydroxyalkylamide group containing compound.

12. Composition according to any of the preceding claims, wherein the binder comprises, based on the total weight of the binder,

35

- (a) 2 to 88.5 parts by weight of the carboxyl group containing amorphous isophthalic acid containing polyester,
- (b) 1 to 85 parts by weight of the carboxyl group containing semi-crystalline polyester,
- (c) 10 to 60 parts by weight of the glycidyl group containing acrylic copolymer, and
- 5 (d) 0.5 to 10.0 parts by weight of the curing agent having functional groups reactive with the polyesters' carboxyl groups.
13. Composition according to any of the preceding claims, further comprising one or more additive(s) selected from the group consisting of catalysts, fillers, flow control agents, degassing
- 10 agents, UV-light absorbers, light stabilizers, antioxidants and other stabilizers.
14. Composition according to any of the preceding claims, further comprising one or more dyes and/or pigments, such as metal oxides, metal hydroxides, metal powders, sulphides, sulphates, carbonates, silicates, carbon black, talc, china clay, barytes, iron blue, lead blue,
- 15 organic reds and organic maroons.
15. Method of preparing a composition as claimed in any of claims 1-14 comprising the steps of blending the components of the composition to prepare a premix, homogenising the premix at an elevated temperature such as 70-150°C and grounding the homogenised product to
- 20 obtain the powdered thermosetting composition.
16. Method according to claim 15, wherein in a first step the amorphous polyester and the semi-crystalline polyester are dry blended or melt blended.
- 25 17. Use of a composition as claimed in any of claims 1-14 as powdered varnish or paint or for the preparation of a powdered varnish or paint.
18. Powdered varnish or paint consisting of or comprising a composition as claimed in any of claims 1-14.
- 30 19. Method of preparing a coating on a substrate comprising the steps of applying a powdered varnish or paint as claimed in claim 18 to the substrate and heating the coated substrate to fuse and cure the powdered varnish or paint to obtain the coating.
- 35 20. Coating, preparable by the method of claim 19.

21. Substrate entirely or partially coated with the coating of claim 20.

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 July 2002 (18.07.2002)

PCT

(10) International Publication Number
WO 02/055620 A3

(51) International Patent Classification⁷: **C09D 167/00**,
133/06, 5/03

(21) International Application Number: PCT/EP01/14888

(22) International Filing Date:
17 December 2001 (17.12.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
00128097.3 21 December 2000 (21.12.2000) EP

(71) Applicant (for all designated States except US): **UCB, S.A.** [BE/BE]; Allée de la Recherche, 60, B-1070 Bruxelles (BE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **MOENS, Luc** [BE/BE]; Ijvogellaan 30, B-1640 Sint-Genesius-Rode (BE). **KNOOPS, Nele** [BE/BE]; Blokweg 12, B-3020 Herent (BE). **MAETENS, Daniel** [BE/BE]; Avenue René Comhaire 108, B-1070 Bruxelles (BE).

(74) Agent: **ROELANTS, François**; UCB, S.A., Intellectual Property Department, Allée de la Recherche, 60, B-1070 Bruxelles (BE).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report:
19 September 2002

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: POWDERED THERMOSETTING COMPOSITION FOR COATINGS

(57) Abstract: The present invention relates to powdered thermosetting compositions including a binder which comprises a carboxyl group containing amorphous isophthalic acid containing polyester, a carboxyl group containing semi-crystalline polyester, at least 10 parts by weight, based on the total weight of the binder, of a specific glycidyl group containing acrylic copolymer and a curing agent having functional groups reactive with the polyesters' carboxyl groups. The powdered thermosetting compositions are useful for the preparation of powdered paints and varnishes which give low gloss coatings having an outstanding flow, a remarkable weatherability and excellent mechanical properties.

WO 02/055620 A3

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 01/14888

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09D167/00 C09D133/06 C09D5/03

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>DATABASE WPI Section Ch, Week 199132 Derwent Publications Ltd., London, GB; Class A28, AN 1991-234980 XP002204854 & JP 03 153771 A (MITSUI TOATSU CHEM INC), 1 July 1991 (1991-07-01) abstract</p>	1
Y	<p>WO 95 01407 A (EASTMAN CHEM CO) 12 January 1995 (1995-01-12) page 11, line 21 -page 12, line 3; claims</p>	1
P,A	<p>EP 1 067 159 A (UCB SA) 10 January 2001 (2001-01-10) claims; examples 17,19,22; table 1</p>	1



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

5 July 2002

Date of mailing of the international search report

23/07/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Deraedt, G

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 01/14888

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
JP 3153771	A	01-07-1991	JP	2764096 B2	11-06-1998
WO 9501407	A	12-01-1995	CA	2166306 A1	12-01-1995
			EP	0706546 A1	17-04-1996
			JP	8512078 T	17-12-1996
			MX	9405012 A1	31-01-1995
			WO	9501407 A1	12-01-1995
EP 1067159	A	10-01-2001	EP	1067159 A1	10-01-2001
			AU	6559700 A	22-01-2001
			WO	0102504 A1	11-01-2001
			EP	1198527 A1	24-04-2002

Form PCT/ISA/210 (patent family annex) (July 1992)